


ENERGIZER 393

ZERO MERCURY

SILVER OXIDE



Industry Standard Dimensions




DESIGNED FOR USE ON CONTINUOUS LOW DRAIN
HIGH PULSE ON DEMAND

Specifications

| | |
|---------------------------|--|
| Chemical System: | Silver Oxide (Zn/Ag ₂ O) |
| Designation: | ANSI-1137SO, IEC-SR48 |
| Nominal Voltage: | 1.55 Volts |
| Typical Capacity: | 75 mAh* (to 1.2 volts) |
| Capacity Test: | 10K ohm continuous drain at 21°C |
| Typical Weight: | 1.12 grams (0.04 oz.) |
| Typical Volume: | 0.26 cubic centimeters (0.16 cubic inch) |
| Impedance (40 Hz): | 20 to 30 ohms |

* Varies according to the applied load, temperature, and cutoff voltage.


Cross Section



Typical Discharge Characteristics

Typical Performance at 21°C (70°F)

Schedule: Continuous
Typical Drain @1.55V:
0.155 milliamperes
Load: 10K ohm




| <u>Schedule</u> | <u>Typical Drains</u> at 1.55V (milliamperes) | <u>Load</u> (ohm) | <u>Cutoff</u> 1.2V (hours) |
|-----------------|---|----------------------|----------------------------------|
| Continuous | 0.155 | 10K | 484 |


Temperature Characteristics

Typical Performance at Low Discharge Rates

Service Effects



Storage Effects



Important Notice

This datasheet contains typical information specific to products manufactured at the time of its publication.
Contents herein do not constitute a warranty and are for reference only.