



DATA SHEET

Type :	Rechargeable Nickel Metal
	Hydride Cylindrical Cell
Recycled material	Rechargeable Nickel Metal Hydride
content	Battery Made with Minimum 10%
	Recycled materials
Nominal Dimension :	Φ = 14.5mm
(with Sleeve)	H = 50.5mm
Applications :	Recommended discharge current
''	130 to 3900 mA
Nominal Voltage :	1.2V
Capacity :	Rated: 1300mAh
	Typical: 1350mAh
	When discharged at 260mA to
	1.0V at 20℃
Charging Condition :	130mA for 16 hrs at 20℃
Charging Retention	80% of nominal capacity after cell
	storage at 20°C for 12 months
	When discharged at 260mA to
	1.0V at 20°C
Fast Charge :	650mA to 1300mA (0.5 to 1C)
rast Charge .	charge termination control
	recommended control parameters:
	-∆V : 0-5mV
	DT/dt : 0.8°C/min (0.5 to 0.9C)
	0.8 - 1°C/min (1C)
	TCO : 45 - 50°C
	Timer : 105% nominal input
	(for ref. only)
Service Life :	>500cycles (IEC61951-2(2017) 7.5.1.2)
	>200cycles (IEC61951-2(2017) 7.5.1.4)
Continuous :	130mA maximum current for 1 year.
Overcharge	No conspicuous deformation and/or
	leakage
Weight :	23.0g
Internal Resistance :	Average 25mΩ upon fully charged
	(Max. 35mΩ) at 1000Hz
Max. Charging Voltage :	1.5V at 130mA charging
Ambient Temperature :	Standard Charge : 0 to 45°C
Range	Fast Charging : 10 to 45°C
	Discharge : -20 to 50°C
	Storage: -20 to 35°C
	Olorage20 to 00 C

Fast Charge (Charge Control Required)




Model No.: GP130AAHCE



Low Rate Discharge Voltage(V) 1.6 1.5 1.4 Charge: 130mA × 16hrs at 20℃ 1.3 1.2 1.1 1 0.9 650mA 130mA 260m A 0.8 (0.5C)(0.1C)(0.2C)0.7 2 8 10 0 6 12 14 Discharge Time (Hrs)

High Rate Discharge



The information (subject to change without prior notice) contained in this document is for reference only and should not be used as a basis for product guarantee or warranty. For applications other than those described here, please consult your nearest GP Sales and Marketing Office or Distributors.

www.gpbatteries.com

MRS6393 rev.1