

## **ESD Flux Bottle**

## **Description:**

New development process of moulding polyethylene bottles utilising a concentrate that does not contain any Ethoxylated Tertiary Amine, which is widely used as an antistatic agent. These ESD safe bottles have an average surface resistivity of  $10^9$  to  $10^{10}\,\Omega$ /Square and do not have any less desirable features associated with surfactant laden material.

These bottles will dissipate a static charge of ±5000V in less than two seconds at 40% relative humidity. By their chemical nature, they will not have any chemical reactivity with solvents as TCE or alcohol. The pH of the deionised water solutions tested were that same before and after a seven day period. No colour change or any other physical change was noted for any solvents tested. Competitively priced with existing static generating containers.



## Features:

- · Static Free
- · Non-Greasy
- · No Tertiary Amines
- · Humidity Independent
- Average Surface Resistivity of 10<sup>9</sup> to 10<sup>10</sup> Ω/Square
- · Helps to Meet ESD-T20.20-2000

| Product Code: | Description:    | Size:                        | Additional Notes: |
|---------------|-----------------|------------------------------|-------------------|
| 146-0001      | ESD Flux Bottle | 2oz Bottle - 26 Gauge Needle | Each              |
| 146-0010      | ESD Flux Bottle | 2oz Bottle - 20 Gauge Needle | Each              |

Important Notice: This data sheet and its contents (the "Information") belong to Antistat or are licensed to it. No licence is granted for the use of it other than for information purposes in connection with the products to which it relates. No licence of any intellectual property rights is granted. The Information is subject to change without notice and replaces all data sheets previously supplied. The Information supplied is believed to be accurate but Antistat assumes no responsibility for its accuracy of the previously supplied and the previously supplor completeness, any error in or omission from it or for any use made of it. Users of this data sheet should check for themselves the Information and the suitability of the angle of the suitability ofproducts for their purpose and not make any assumptions based on information included or omitted. Liability for loss or damage resulting from any reliance on the products for their purpose and not make any assumptions based on information included or omitted. $Information or use of it (including liability resulting from negligence or where Antistat was aware of the possibility of such loss or damage arising) is excluded. \\ @Antistat.$ 









WWW.ANTISTAT.CO.UK